



PLASTIC MEDIA

BLAST & PEEN SERVICES PTE LTD
11 Tuas South Link 1
#03-18 SHINE@TUAS SOUTH | Singapore 636901

Office Phone
+65 8811 1883

Handphone
+65 9850 0121

Email Address
sales@bnp.com.sg

Website
www.bnp.com.sg



DESCRIPTION

Plastic Media is a non aggressive granulated plastic abrasive for use in applications where the underlying substrate cannot be damaged. Plastic Media is used for coating removal and stripping, cleaning, deburring and deflashing.

Plastic Media is produced in a variety of plastic types, hardness's and sizes to suit the application. Plastic Media can be used on soft and thin substrates, composites, aluminium, fiberglass and delicate parts without causing damage to the part

APPLICATION

Dry stripping of coatings from aluminium, composite and steel aeronautical structures and components, ie fuselage, landing gear, engine casing and engine blades.

Removal of powder coatings from aluminium and steel components without damage to underlying substrate or galvanized coating. Selective layer paint removal.

Deburring and deflashing of electronic components incl. resin bleed removal from leadframes. Mould cleaning and automotive paint removal



Size in Details

Grit No.	12/16	12/20	16/20	20/30
Size in inch	0.047 - 0.066	0.033 - 0.066	0.033 - 0.047	0.023 - 0.033
Size in μm	1200 - 1700	800 - 1700	800 - 1200	600 - 800

Grit No.	20/40	30/40	40/60	60/80
Size in inch	0.017 - 0.033	0.017 - 0.023	0.010 - 0.017	0.007 - 0.010
Size in μm	400 - 800	400 - 600	250 - 400	180 - 250v

Other sizes and specifications available upon request.

Physical Properties

Type	Hardness	Specific Gravity	Bulk Density	Shape	Colour
II - Urea	3.5 Mohs	1.47 - 1.52 g/cm ³	929-961 kg/m ³	Angular	Multi
III - Melamine	4.0 Mohs	1.5 g/cm ³	700 kg/m ³	Angular	Multi
V - Acrylic	3.0 Mohs	1.1 - 1.2 g/cm ³	640 - 800 kg/m ³	Angular	Multi

Specification

Aerospace Manufactured and certified to MIL-P-85891A specifications.
United States Military approved source. Rolls Royce CSS227 - Type C .
Industrial Manufactured to in-house industrial specification. For non Mil Spec requirement use.