



# ***STAINLESS STEEL CUT WIRE***

**BLAST & PEEN SERVICES PTE LTD**

11 Tuas South Link 1

#03-18 SHINE@TUAS SOUTH | Singapore 636901

Office Phone  
+65 8811 1883

Handphone  
+65 9850 0121

Email Address  
sales@bnp.com.sg

Website  
www.bnp.com.sg



## **i** DESCRIPTION

Stainless Steel Cut Wire is produced by cutting stainless steel wire into pellets, the length equal to the diameter of the wire. Stainless Steel Cut Wire is available manufactured from 304 and 430 series stainless steels.

Stainless Steel Cut Wire is available as cut for finishing processes and conditioned to G3 Spherical Conditioned for peening applications. Due to the solidity of each particle, Stainless Steel Cut Wire has a longer life than cast stainless steel shot

## **+** APPLICATION

Deflashing, deburring and surface finishing of aluminium castings and die castings without imparting ferrous particles and dust onto the surface that can discolour.

Shot peening of non ferrous components that cannot tolerate any ferrous contamination. Shot peening repeatability is improved due to durability of the particles.

Surface finishing of a variety of stainless steel fabrications and castings, producing a bright luster, orange peel finish.



### Size in Details

Shot No.	SSCW0.3	SSCW0.4	SSCW0.5	SSCW0.6	SSCW0.7	SSCW0.8
Size in mm	0.3	0.4	0.5	0.6	0.7	0.8

  

Shot No.	SSCW1.0	SSCW1.2	SSCW1.5	SSCW2.0	SSCW2.5
Size in mm	1.0	1.2	1.5	2.0	2.5

### Physical Properties

Specific Gravity	Bulk Density	Colour
7.6 g/cm <sup>3</sup>	≈ 4400kg/m <sup>3</sup>	Silver

### Typical Chemical Composition

Type	Chromium	Nickel	Carbon	Silicon
304	16 - 20%	8 - 10%	0.06 - 0.08%	1.5 - 2.0%
430	16 - 18%	-	≤0.1%	≤1.2%

Type	Manganese	Phosphorus	Sulfur
304	0.9 - 1.2%	≤0.45%	≤0.3%
430	≤1.0%	≤0.45%	≤0.3%

### Hardness

Type	HV	HRC
304	400 - 500	40 - 50
430	300 - 450	30 - 45

### Shape

G0	G1
As cut	Conditioned

### Specifications

AMS-2431/4